

Polyether block amide **PEBAX® MH 2030** is a thermoplastic elastomer made of flexible polyether and rigid polyamide. MH 2030 is an inherently dissipative polymer and can be dry blended or compounded with an isolative polymer to lower the surface resistivity.

Main Characteristics	Value	Unit	Test Method
Density	1.14	g/cm ³	ISO 1183
Water Absorption at Equilibrium At 20°C and 50 % RH	4.5	%	ISO 62
Water Absorption At 23°C and 24 h in water	120	%	
Melting Point	204	°C	ISO 11357
Hardness Shore (*) Instantaneous	40	Shore D	ISO 868
Flexural Modulus (*)	80	MPa	ISO 178
Surface Resistivity (*)	1 10⁷	Ω / sq	IEC 60093
Volume Resistivity (*)	1 10⁷	Ω.cm	IEC 60093
Refractive Index	1.508	–	Internal method

(*) Samples conditioned 15 days at 23°C - 50 % R.H.

DPT/TDS/August 2009

The information contained in this document is based on trials carried out by our Research Centres and data selected from the literature, but shall in no event be held to constitute or imply any warranty, undertaking, express or implied commitment from our part. Our formal specifications define the limit of our commitment. No liability whatsoever can be accepted by Arkema with regard to the handling, processing or use of the product or products concerned which must in all cases be employed in accordance with all relevant laws and/or regulations in force in the country or countries concerned.